

MICHIGAN LIMESTONE OPERATIONS INC.
 PORT INLAND PLANT
 STATE PIT NO. 75-05

TYPICAL PHYSICAL PROPERTIES OF PORT INLAND LIMESTONE

	MI-6AA OH-57	MI-17A OH-67	MI-31A OH-8
Bulk Specific Gravity	2.67	2.67	2.68
Absorption	.47	.49	.56
L.A. Abrasion	29.80	29.10	26.20
Soundness (Sodium)	4.60	2.80	2.60
Chert Particles	0.0	0.0	0.0
Total Deleterious	0.0	0.0	0.1
Crushed Particles	100%	100%	100%
Freeze Thaw.....			97%
(per 244 cycles-Relative Dynamic Modulus)			
Alkali Reactivity.....			0.0
Chloride Analysis			
Acid Soluble.....			.021
Water Soluble.....			.008